

Luran 338L

Styrene Acrylonitrile (SAN)

TECHNICAL DATASHEET

DESCRIPTION

Luran® 338L is an easy-flow grade of SAN, suitable for moldings with very thin walls and / or adverse flow length to wall ratio. It features excellent transparency, a light intrinsic color and very good color consistency.

FEATURES

- Excellent transparency
- Light natural color
- Good surface appearance
- Extremely easy flow

APPLICATIONS

- Cosmetic packaging

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate 220 °C/10 kg	ISO 1133	cm ³ /10 min	40
Mechanical Properties			
Izod Notched Impact Strength, 23 °C	ISO 180/A	kJ/m ²	2
Izod Notched Impact Strength, -30 °C	ISO 180/A	kJ/m ²	2
Izod Unnotched Impact Strength	ISO 180	kJ/m ²	14
Charpy Notched Impact Strength, 23° C	ISO 179	kJ/m ²	1.7
Charpy Notched Impact Strength, -30 °C	ISO 179	kJ/m ²	1.5
Charpy Unnotched, 23 °C	ISO 179	kJ/m ²	14.5
Charpy Unnotched, -30 °C	ISO 179	kJ/m ²	15
Tensile Strain at Break, 23 °C	ISO 527	%	2
Tensile Modulus	ISO 527	MPa	3500
Hardness, Rockwell		M scale	67
Hardness, Ball Indentation	ISO 2039-1	MPa	162
Thermal Properties			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	105
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	86
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	98

Luran 338L

Styrene Acrylonitrile (SAN)

TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Coefficient of Linear Thermal Expansion	ISO 11359	10 ⁻⁶ /°C	63
Thermal Conductivity	DIN 52612-1	W/(m K)	0.17
Electrical Properties			
Dielectric Constant (100 Hz)	IEC 60250	-	3
Dissipation Factor (100 Hz)	IEC 60250	10 ⁻⁴	47
Dissipation Factor (1 MHz)	IEC 60250	10 ⁻⁴	64
Volume Resistivity	IEC 60093	Ohm*m	>1E13
Surface Resistivity	IEC 60093	Ohm	>1E14
Optical Properties			
Refractive Index, Sodium D Line	ISO 489	-	1.569
Light Transmission at 550 nm	ASTM D 1003	%	>89
Haze	ASTM D 1003	%	<1
Other Properties			
Density	ISO 1183	kg/m ³	1080
Moisture Absorption, Equilibrium 23 °C/50% RH	ISO 62	%	0.2
Processing			
Linear Mold Shrinkage	ISO 294-4	%	0.3 - 0.7
Melt Temperature Range	ISO 294	°C	200 - 250
Mold Temperature Range	ISO 294	°C	40 - 80
Drying Temperature		°C	80
Drying Time		h	4

Typical values for uncolored products

DISCLAIMER

The above information is provided in good faith. INEOS Styrolution is not responsible for any processing or compounding which may occur to product finished articles, packaging materials or their components. Further, INEOS Styrolution MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN OR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user.