

Typical Engineering Properties of High Density Polyethylene

General Properties	English Units	SI Units
CAS Number	25213-02-9	25213-02-9
Molecular Weight	0.062 lbs	28.0 g
Density	0.0336-0.0349 lbs/in ³	0.930-0.965 g/cm ³
Melt Density	0.027 lbs/in ³	0.764 g/cm ³
Bulk Density		
Pellets	35 – 38 lbs./ft ³	561 - 609 kg/m ³
Flake	31 – 34 lbs./ft ³	497 – 545 kg/m ³
Permeability Coefficients:		
Water (@ 25°C)	1.7x10 ⁻¹² in ² /sec ² -atm	1.3x10 ⁻¹⁰ cm ² /(sec-cm Hg)
Oxygen (@ 30°C)	1.4x10 ⁻¹² in ² /sec ² -atm	1.06x10 ⁻¹⁰ cm ² /(sec-cm Hg)
Carbon Dioxide (@ 30°C)	4.6x10 ⁻¹² in ² /sec ² -atm	3.5x10 ⁻¹⁰ cm ² /(sec-cm Hg)
Nitrogen (@ 30°C)	0.35x10 ⁻¹² in ² /sec ² -atm	0.27x10 ⁻¹⁰ cm ² /(sec-cm Hg)
Water Absorption @ 24 h Immersion	0.03%	0.03%
Mechanical Properties		
Modulus of Elasticity (Young's Modulus)		
Homopolymer	150,000 psi	1,035 N/mm ²
Copolymer	60,000 – 145,000 psi	400 – 1,000 N/mm ²
Poisson's Ratio	0.40 - 0.45	0.40 - 0.45
Hardness, Shore D Scale	55 – 70	55 – 70
Coefficient of Friction	0.29	0.29
Thermal Properties		
DSC Melting Point		
Homopolymer	275 °F	135 °C
Copolymer	230 – 273 °F	110 – 134 °C
Specific Heat (@ 23°C)		2.25 kJ/kg °K
Heat of Fusion		
Homopolymer		245 kJ/kg
Copolymer		140 – 232 kJ/kg
Thermal conductivity		
Homopolymer		0.49 W / m °K
Copolymer		0.40 – 0.47 W / m °K
Vicat Softening Temperature		
Homopolymer	270 °F	132 °C
Copolymer	233 – 266 °F	112 – 130 °C
Coefficient of Linear Thermal		
Expansion	12 x 10 ⁻⁵ in/(in °F)	12 x 10 ⁻⁵ cm/(cm °C)
Shrinkage	0.018 -0.020 in/in	0.018 – 0.020 cm/cm

Typical Engineering Properties of High Density Polyethylene

Flammability Properties	English Units	SI Units
Auto-ignition Temperature	>650 °F	>340 °C
Energy Required for Ignition		>2,500 kJ/m ²
Fuel Value Content	19,900 BTU/lb.	
Ignition Temperature – Cloud	790 °F	420 °C
Minimum Radiant Flux for Ignition		20 kW/m ²
Smoke Specific Extension Area	1,855 – 3,320 ft ² /lb.	380 – 610 m ² /kg
Soot Yield	0.06–0.09 lbs. soot/lb polymer	0.03–0.04 kg soot/kg polymer
Electrical Properties	English Units	SI Units
Volume Resistivity	6 x 10 ⁵ Ohm-cm	6 x 10 ⁵ Ohm-cm
Dielectric Constant	2.30 – 2.32 x 10 ⁵ Hertz	2.1 – 2.3 x 10 ⁵ Hertz
Dielectric Strength	600 – 700 Volts/mil	600 – 700 Volts/mil
Power Factor	<0.0001 kHz	<0.0001 kHz
Dissipation Factor		
@ 10 kHz	<0.0005 h	<0.0005 h
@ 1 MHz	<0.0005 h	<0.0005 h
@ 1 GHz	<0.0005 – 0.002 h	<0.0005 – 0.002 h
Arc Resistance	136 – 185 s	136 – 185 s

Data gathered from numerous literature sources over a number of years and is presented as obtained with no guarantees as to the accuracy of the data. Unless otherwise noted, all properties are those of the bulk material at ambient temperature.

Product inquiries:

Marina View Headquarters
2600 South Shore Blvd.
Suite 500
League City, Texas 77573
Telephone: 281-535-6600
Fax: 281-535-6764
Customer Service: 800-527-5419

Battleground Manufacturing Complex
1230 Independence Parkway South
La Porte, Texas 77571
Telephone: 713-307-3000
Fax: 713-307-3521
Technical Center: 800-338-0489

www.ineos-op.com

<http://ordersonline.ineos-op.com>

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. As conditions of use may vary and are beyond the control of INEOS Olefins & Polymers USA, no representations or warranty, express or implied, are made with respect to the accuracy, reliability, or completeness of the this information. This information in no way modifies, amends, enlarges, or creates any specification or warranty, and ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE HEREBY EXCLUDED. INEOS Olefins & Polymers USA shall not be responsible for any damage or injury resulting from abnormal use, from any failure to follow appropriate practices, or from hazards inherent in the nature of the product and/or material, nor for toxicological effects or Industrial Hygiene associated with particular use of any product described herein. This information relates only to the specific product and/or material designated and may not be valid for such product and/or material used in combination with any other product and/or material or in any process, unless otherwise specified. This information shall not be construed as a recommendation for any use that may infringe any patent, trademark, or the like, or as an endorsement of any material, equipment, service, or other item not supplied by INEOS Olefins & Polymers USA.

The name and logo INEOS are trademarks of the INEOS Group and its affiliated companies and businesses.

INEOS
Olefins & Polymers USA