

Lustran 620

Acrylonitrile Butadiene Styrene (ABS)

**TECHNICAL
DATASHEET**

DESCRIPTION

Lustran® 620 is a high modulus, HFC 134a and HCFC 22 resistant extrusion grade resin designed for refrigerator door and food liners. It offers good melt strength and deep draw formability for superior material distribution in large complex parts.

FEATURES

- Superior deep draw formability for large complex parts
- Good melt strength
- High tensile modulus
- HFC 134a and HCFC 22 resistant
- UL 94 HB rated
- FDA regulation 21 CFR 181.32 compliant

APPLICATIONS

- Refrigerator doors
- Food liners

Property, Test Condition	Standard	Unit	Values
--------------------------	----------	------	--------

Typical values for uncolored products

SUPPLY FORM

Lustran® ABS (Acrylonitrile Butadiene Styrene) resins are available in bulk railcar, bulk truckload and 726kg box quantities.

REGULATORY COMPLIANCE

Please refer to Styrolution web site or contact Styrolution Technical Service for further information.

PROCESSING

To obtain an optimum balance of sheet gloss and mechanical properties, the extruder profile should be set to deliver polymers at a melt temperature between 420° and 465°F (215° and 240°C).

PRODUCT SAFETY

Safety Data Sheets and product labels provide information concerning the health and safety precautions that must be observed when handling the Styrolution products mentioned in this publication. No adverse effects on the health of processing personnel have been observed if the products are correctly processed and the production areas are suitably ventilated. For styrene, acrylonitrile, alpha-methyl styrene, maleic anhydride and 1, 3-butadiene, the maximum allowable workplace concentrations must be observed according to current local and federal regulations. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. This information is available in safety data sheets and on product labels. If there are questions or concerns, consult your Styrolution representative or contact the Product Safety and Regulatory Affairs Department at Styrolution.

DISCLAIMER

The aforementioned data shall constitute the agreed contractual quality of the product sold by INEOS Styrolution at the time of passing of risk. INEOS Styrolution does not make any further warranty, representation or guarantee of any kind, express or implied, regarding the suitability of the product for any particular purpose or application and INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.
