

LUSTRAN[®] ABS 308

ABS

Medical Grade

Description

Lustran ABS 308 resin is a low gloss, easy-flowing grade of ABS (acrylonitrile butadiene styrene). This injection molding grade offers a good balance of rigidity, impact strength, and abuse resistance. The base resin used in the Lustran ABS 308 product meets FDA modified ISO 10993-1 requirements as well as U.S. Pharmacopeia 23 Class VI test requirements. The resin is available in natural (000000).

Applications

Lustran ABS 308 resin is designed for applications requiring a good balance of physical properties and a low-gloss appearance. Typical applications include components of intravenous (IV) systems, diagnostic test kits, and surgical instruments. As with any product, use of Lustran ABS 308 resin in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability.

Biocompatibility

Lustran ABS 308 resin is designated as “medical-grade” and has met the requirements of the FDA-Modified ISO 10993, Part I “Biological Evaluation of Medical Devices” tests with human tissue contact time of 30 days or less.

Only medical-grade resins may be considered as candidates for applications requiring biocompatibility.

Regrind must not be used in medical applications requiring biocompatibility.

Manufacturer’s Responsibility

It is the responsibility of the medical device, biological product, or pharmaceutical manufacturer (“Manufacturer”) to determine the suitability of all component parts and raw materials, including Lustran ABS 308 resin, used in its final product in order to ensure safety and compliance with FDA requirements. This determination must include, as applicable, testing for suitability as an implant device and suitability as to contact with and/or storage of human tissue and liquids including, without limitation, medication, blood, or other bodily fluids.

Under no circumstances may Lustran ABS 308 resin be used in any cosmetic, reconstructive, or reproductive implant applications. Nor may Lustran ABS 308 resin be used in any other bodily implant applications, or any applications, or any applications involving contact with or storage of human tissue, blood, or other bodily fluids, for greater than 30 days, based on FDA-Modified ISO 10993, Part I “Biological Evaluation of Medical Devices” tests.

The suitability of an INEOS ABS product in a given end-use environment is dependent upon various conditions including, without limitation, chemical compatibility, temperature, part design, sterilization method, residual stresses, and external loads. It is the responsibility of the Manufacturer to evaluate its final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Single-use medical devices made from an INEOS ABS product are not suitable for multiple uses. If the medical device is designed for multiple uses, it is the responsibility of the Manufacturer to determine the appropriate number of permissible uses by evaluating the device under actual sterilization and end-use conditions and to adequately advise and warn purchasers and users thereof.

Sterilization

Parts molded from Lustran ABS 308 resin are sterilizable using radiation or ethylene oxide. Steam sterilization is not suitable due to the resin’s insufficient heat resistance. The sterilization method and the number of sterilization cycles a part made from Lustran ABS 308 resin can withstand will vary depending upon type or grade of resin, part design, processing parameters, sterilization temperature, and chemical environment. Therefore, the Manufacturer must evaluate each device to determine the sterilization method and the number of permissible sterilization cycles appropriate for actual end-use requirements and must adequately advise and warn purchasers and users thereof.

Drying

Drying prior to processing is recommended in a desiccant dehumidifying hopper dryer. An inlet air dew point of -20°F (-29°C) or below is recommended to achieve a moisture content ≤ 0.1%. Typical drying conditions are 2 hours at 180°-190°F (82°-88°C). Drying for 4 hours at 160°-170°F (71°-77°C) is also adequate.

Processing

A reciprocating screw injection molding machine is preferred. A general-purpose screw with a 2.5:1 compression ratio is suggested. A minimum L/D ratio of 20:1 will ensure melt homogeneity.

Lustran ABS 308 resin can be molded over a wide range of melt temperatures and will maintain its low gloss performance. For best part quality, use the lower range of the recommended melt temperature with minimum barrel residence time. To avoid excessive residence time in the barrel, volume and weight of the shot should be balanced against barrel capacity and injection stroke. A shot weight-to-machine capacity ratio of 0.5–0.75 is recommended.

A mold temperature of 110°-150°F (45°-65°C) is recommended for minimum gloss development, with the lower end of this range preferred for smooth tools. A higher mold temperature is preferred for replication of the tool surface in textured tools.

Typical processing parameters are noted below. Actual processing conditions will depend on machine size, mold design, material residence time, and shot size.

Typical Injection Molding Conditions

Barrel Temperatures:	
Rear.....	455°– 480°F (235°– 250°C)
Middle.....	465°– 490°F (240°– 255°C)
Front.....	475°– 500°F (245°– 260°C)
Nozzle.....	475°– 500°F (245°– 260°C)
Melt Temperature.....	475°– 510°F (245°– 265°C)
Mold Temperature.....	110°– 150°F (45°– 65 °C)
Injection Pressure.....	10,000 – 16,000 psi
Hold Pressure.....	.50 – 75% of Injection Pressure
Back Pressure.....	.50 – 100 psi
Screw Speed.....	Moderate
Injection Speed.....	High
Cushion	1/4 in max
Clamp.....	.2 – 4 ton/in ²

Achieving uniform surface appearance on a molded part requires proper tool design, properly prepared and conditioned tool cavity surfaces and preventative maintenance. Tool design should include adequate, properly sized and properly designed vents. Preventative maintenance for tooling requires, but is not limited to, periodic inspection and cleaning of tool surfaces, actual cavity surfaces and cavity vents. Additional information on processing may be obtained by contacting an INEOS ABS technical service representative.

Regulatory Compliance Information

Some of the end uses of the product described in this bulletin must comply with applicable regulations, such as FDA, NSF, USDA, and CPSC. If you have any questions on the regulatory status of this product, contact your INEOS ABS representative or Regulatory Affairs Manager at INEOS ABS.

Health and Safety Information

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling the INEOS ABS products mentioned in this publication. For materials mentioned which are not INEOS ABS products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be followed. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., *material safety data sheets and product labels*. Consult your INEOS ABS representative or contact the Product Safety and Regulatory Affairs Department at INEOS ABS.

Typical Properties* for Natural Resin	ASTM Test Method (Other)	Lustran® ABS 308 Resin	
		U.S. Conventional	SI Metric
General Specific Gravity Density Specific Volume Mold Shrinkage Melt Flow Rate at 230°C/3.8-kg Load Melt Flow Index at 220°C/10-kg Load	D 792 D 792 D 792 D 955 D 1238	1.05 0.038 lb/in ³ 26.4 in ³ /lb 0.004 – 0.007 in/in	1.06 g/cm ³ 0.95 cm ³ /lb 0.004 – 0.007 mm/mm
Mechanical Tensile Stress at Yield Tensile Modulus Flexural Stress at Yield Flexural Modulus Impact Strength, Notched Izod: 0.125-in (3.2-mm) Thickness 73°F (23°C) Rockwell Hardness, R Scale	D 638 D 638 D 790 D 790 D 256 D 785	5,250 lb/in ² 320,000 lb/in ² 10,500 lb/in ² 355,000 lb/in ² 3.2 ft-lb/in	36 MPa 2.2 GPa 72 MPa 2.4 GPa 171 J/m
Thermal Deflection Temperature Under Load: 0.125-in (3.2-mm) Thickness Unannealed 264 psi (1.82 MPa) 66 psi (0.46 MPa) Annealed 264 psi (1.82 MPa) 66 psi (0.46 MPa) 0.5-in (12.7-mm) Thickness Unannealed 264 psi (1.82 MPa) 66 psi (0.46 MPa) Annealed 264 psi (1.82 MPa) 66 psi (0.46 MPa) Coefficient of Linear Thermal Expansion Vicat Softening Temperature, Rate B	D 648 D 696 D 1525	168°F 192°F 203°F 212°F 189°F 198°F 212°F 216°F 5.0 E-05 in/in/°F 223°F	75°C 88°C 95°C 100°C 87°C 92°C 100°C 102°C 9.0 E-05 mm/mm/°C 106°C

* These items are provided as general information only. They are approximate values and are not part of the product specifications.

Note: The information contained in this publication is current as of May 2012. Please contact INEOS ABS to determine whether this publication has been revised.

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

INEOS
ABS

INEOS ABS (USA) Corporation
INEOS ABS NAFTA
356 Three Rivers Parkway
Addyston, OH 45001

www.ineos-abs.com