

Lustran® ABS 349

Product Description

Lustran ABS 349 is a high-gloss, medium-impact injection molding resin that has been specially formulated for excellent surface lubricity using internal additives.

<i>Typical Properties*</i>	<i>Cond.</i>	<i>Units</i>	<i>Value</i>	<i>ASTM</i>
Tensile Stress @ Yield	73°F	psi	6,100	D638
Tensile Modulus	73°F	psi	380,000	D638
Flexural Stress @ Yield	73°F	psi	10,500	D790
Flexural Modulus	73°F	psi	390,000	D790
Izod Impact, notched 1/8" x 1/2" bar	73°F	ft.-lb./in	5.0	D256
	-40°F	ft.-lb./in.	-	
Hardness – Rockwell	73°F	R	110	D785
Specific Gravity	73°F		1.05	D792
Deflection Temperature Under Load, 1/2" x 1/2" bar Unannealed				D648
	264 psi	°F	190	
	66 psi	°F	-	
	Annealed			
	264 psi	°F	-	
	66 psi	°F	-	
Vicat Softening Point	1 kg	°F	220	D1525
Melt Flow**	230/3.8	g/10 min	6	D1238
Coefficient of Linear Expansion		in./in./ °F	4.5 x 10 ⁻⁵	D696
Mold Shrinkage		in./in.	0.004 – 0.006	D955

*Typical properties are provided as general information only. They are approximate and are not part of the product specifications.

**For information on using melt flow as a quality control procedure, see INEOS ABS processing literature.

Injection Molding Guidelines for Lustran® ABS 349 ⁽¹⁾

Actual conditions used for processing will depend on machine size, mold design, material residence time and shot size. Pre-drying is recommended.

Stock Temperature ⁽²⁾	475 – 525°F
Drying Conditions ⁽³⁾	2 hours @ 180 – 190°F
Back Pressure	0 – 25 psi
Screw Speed	Moderate
Mold Temperature ⁽⁴⁾	80 – 150°F
Injection Rate	High
Cushion ⁽⁵⁾	0.125" max
Screw Delay	To minimize residence ⁽⁶⁾

- ⁽¹⁾ A reciprocating screw injection molding machine is preferred. A general purpose screw with a 2.5:1 compression ratio is suggested. A minimum L/D of 20:1 will insure melt homogeneity.
- ⁽²⁾ Use minimum stock temperature with minimum barrel residence time, consistent with good part quality. Measure stock temperature with pre-heated, hand-held pyrometer.
- ⁽³⁾ Pre-drying is recommended in a dryer with circulating, dehumidified hot air. The inlet air dewpoint should be -20°F or below. Drying for 4 hours at 160 – 170°F is also adequate.
- ⁽⁴⁾ Mold temperature of 110 – 150°F is recommended for development of maximum gloss and strength.
- ⁽⁵⁾ Maintain ram forward (Packing) time at minimum required to control sink marks.
- ⁽⁶⁾ To avoid excessive residence time, volume and weight of shot should be balanced against barrel capacity and injection stroke. A shot weight-to-machine capacity ratio of 0.5 to 0.75 is recommended.

Health and Safety Information

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling the INEOS ABS products mentioned in this publication. For materials mentioned which are not INEOS ABS products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be followed. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. Information is available in several forms, *e.g., material safety data sheets and product labels*. Consult your INEOS ABS representative or contact the Product Safety and Regulatory Affairs Department at INEOS ABS.

INEOS ABS (USA) Corporation · 356 Three Rivers Parkway · Addyston, OH 45001 · www.ineos-abs.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.