

LUSTRAN[®] Guardian[™] ABS 620

ABS

Extrusion Grade

Product Description

Lustran Guardian ABS 620 is a high modulus, HFC 134a and HCFC 22 resistant extrusion grade resin designed for refrigerator door and food liners. Lustran ABS 620 offers good melt strength and deep draw formability for superior material distribution in large complex parts.

Typical Properties*	ASTM Test Method (Other) ^a	Lustran [®] 620 ABS Resin	
		U.S. Conventional	SI Metric
General			
Specific Gravity	D 792		1.10
Gardner Gloss, 60°			98
Critical Strain (50/50 CO/OA), 73°F	(Stolki)		0.62%
Mechanical			
Tensile Stress at Yield, 73°F	D 638	5,600 lb/in ²	38.6 MPa
Tensile Stress at Fail, 73°F	D 638	4,600 lb/in ²	31.7 MPa
Tensile Modulus, 73°F	D 638	380,000 lb/in ²	2.62 GPa
Elongation at Fail, 73°F	D 638		45%
Flexural Stress at Yield, 73°F	D 790	10,200 lb/in ²	70.4 MPa
Flexural Modulus, 73°F	D 790	350,000 lb/in ²	2.42 GPa
Impact Strength:	D 256		
73°F			
0.125-in Thickness		5.1 ft-lbs _i /in	28.7 kJ/m ²
0°F			
0.125-in Thickness		1.7 ft-lbs _i /in	9.6 kJ/m ²
Multiaxial Impact, Driven Dart (0.5-in dart, 1.5" ring)	(Ceast)		
73°F			
E _{max}		25 ft-lbs _i	34 J
E _{tot}		35 ft-lbs _i	47 J
0°F			
E _{max}		10 ft-lbs _i	14 J
E _{tot}		11 ft-lbs _i	15 J
Thermal			
Heat Deflection Temperature, Annealed	D 648		
264 psi		208°F	98°C
Flammability**			
Flame Class Rating	(UL94)		
1.0 mm			HB

* These items are provided as general information only. They are approximate values and are not part of the product specifications.

Data obtained on extruded sheet specimens, prepared and evaluated at the same time, using the same test procedures, at 73°F and 50% RH, unless otherwise noted.

** Flammability results are based on small-scale laboratory tests for purposes of relative comparison and are not intended to reflect the hazards presented by this or any other material under actual fire conditions.

Suggested Processing Conditions

Dryer

Lustran ABS can be successfully extruded into quality sheet when the total moisture by weight is 0.03% maximum. Suggested drying conditions are 3 to 4 hours at 180°-200°F (82°-90°C) dew point air.

Extruder

To obtain optimum sheet mechanical properties, the extruder profile should be set to deliver polymer with a stock temperature between 460° and 500°F (238° to 260°C). Maintaining constant regrind level and particle size to the extruder feedstock will provide optimum extrusion consistency at a given extrusion profile.

Screw Design

Single- or two-stage screws can be used to extrude these products although a two-stage screw with a vacuum vent is the preferred setup. For two-stage screws, a first-stage compression ratio of 2.5 to 2.7 and a pump ratio of 1.5 to 2.0 are recommended.

Die

Die temperature settings for Lustran Guardian ABS normally range between 410°-485°F (210°-250°C). The die should be adjusted to provide uniform polymer melt at the lips. Maintaining constant regrind level to the extruder feedstock will improve gauge consistency at a given temperature profile.

Roll Stack

Suggested polishing roll settings for Lustran Guardian ABS, for a standard down stack setup are: Top - 200°F (93°C); middle - 165°F (74°C); and bottom - 200°F (93°C). Specific settings will change depending on sheet gauge and linear speed.

Health and Safety Information

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling the INEOS ABS products mentioned in this publication. For materials mentioned which are not INEOS ABS products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be followed. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. Information is available in several forms, *e.g., material safety data sheets and product labels*. Consult your INEOS ABS representative or contact the Product Safety and Regulatory Affairs Department at INEOS ABS.

Note: The information contained in this publication is current as of July 2012. Please contact INEOS ABS to determine whether this publication has been revised.

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

INEOS ABS

INEOS ABS (USA) Corporation
INEOS ABS NAFTA
356 Three Rivers Parkway
Addyston, OH 45001

www.ineos-abs.com