

Lustran LGA

Acrylonitrile Butadiene Styrene (ABS)

TECHNICAL DATASHEET

DESCRIPTION

Lustran® LGA resin is a low-gloss grade of ABS (acrylonitrile butadiene styrene). This automotive injection molding grade offers an excellent balance of rigidity, impact strength, and abuse resistance.

FEATURES

- SAE J1685: ABS0111
- Low gloss
- High flow
- Abuse resistant
- Balance of rigidity and impact strength
- UL 94 HB rated

APPLICATIONS

- Pillars
- Consoles
- Scuff plate
- Interior quarter trim panels

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Flow Rate, 230 °C/3.8 kg	ASTM D 1238	g/10 min	7
Melt Flow Rate, 220 °C/10 kg	ASTM D 1238	g/10 min	21
Mechanical Properties			
Izod Notched Impact Strength, 23 °C (73 °F)	ASTM D 256	ft-lb/in	3.2
Tensile Stress at Yield, 23 °C	ASTM D 638	psi	5300
Tensile Modulus	ASTM D 638	psi x 10 ³	320
Flexural Modulus, 23 °C	ASTM D 790	psi x 10 ³	350
Flexural Stress at 5% Deflection	ASTM D 790	psi	10500
Hardness, Rockwell	ASTM D 785	R scale	105
Thermal Properties			
Vicat Softening Temperature, B/1 (120 °C/h, 10N)	ASTM D 1525	°F	225
DTUL @ 264 psi - Unannealed	ASTM D 648	°F	169
DTUL @ 66 psi - Unannealed	ASTM D 648	°F	194
DTUL @ 264 psi - Annealed	ASTM D 648	°F	203
DTUL @ 66 psi - Annealed	ASTM D 648	°F	212

Lustran LGA

Acrylonitrile Butadiene Styrene (ABS)

TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Coefficient of Linear Thermal Expansion	ASTM D 696	10 ⁻⁴ /°F	0.5
Other Properties			
Density	ASTM D 792	lb/in ³	1.05
Processing			
Linear Mold Shrinkage	ASTM D 955	in/in	0.004 - 0.006
Drying Temperature	-	°F	175
Drying Time	-	h	2 - 4

Typical values for uncolored products

SUPPLY FORM

Lustran® ABS (Acrylonitrile Butadiene Styrene) resins are available in bulk railcar, bulk truckload and 726kg box quantities.

REGULATORY COMPLIANCE

Please refer to Styrolution web site or contact Styrolution Technical Service for further information.

PROCESSING

A reciprocating screw injection molding machine is preferred. A general-purpose screw with a 2.5:1 compression ratio is suggested. A minimum L/D ratio of 20:1 will ensure melt homogeneity. For best part quality, use the lower range of the recommended melt temperature with minimum barrel residence time. To avoid excessive residence time in the barrel, volume and weight of the shot should be balanced against barrel capacity and injection stroke. A shot weight-to-machine capacity ratio of 0.5-0.75 is recommended. A mold temperature of 110°-150°F (45°-65°C) is recommended for development of maximum gloss and strength, with the hotter end of this range preferred.

PRODUCT SAFETY

Safety Data Sheets and product labels provide information concerning the health and safety precautions that must be observed when handling the Styrolution products mentioned in this publication. No adverse effects on the health of processing personnel have been observed if the products are correctly processed and the production areas are suitably ventilated. For styrene, acrylonitrile, alpha-methyl styrene, maleic anhydride and 1, 3-butadiene, the maximum allowable workplace concentrations must be observed according to current local and federal regulations. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. This information is available in safety data sheets and on product labels. If there are questions or concerns, consult your Styrolution representative or contact the Product Safety and Regulatory Affairs Department at Styrolution.

DISCLAIMER

Lustran LGA

Acrylonitrile Butadiene Styrene (ABS)

TECHNICAL
DATASHEET

The aforementioned data shall constitute the agreed contractual quality of the product sold by INEOS Styrolution at the time of passing of risk. INEOS Styrolution does not make any further warranty, representation or guarantee of any kind, express or implied, regarding the suitability of the product for any particular purpose or application and INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.
