

# Eltex® MED 100-MG12

## Product Technical Information

Polypropylene-Homopolymer for Medical & Pharmaceutical injection moulding

Eltex® MED 100-MG12 is a non-nucleated polypropylene homopolymer intended for injection moulding converting processes requiring medium melt flow and good dimensional stability.

Eltex® MED 100-MG12 is produced according to Good Manufacturing Practices, and is available in granular form.

## Applications

Eltex® MED 100-MG12 is especially recommended for the manufacture by injection moulding of Caps & Closures intended for the primary packaging of medical and pharmaceutical applications.

Properties		Test Methods	Values	Units
<b>Physical</b>				
Melt Flow Rate	230°C/2.16kg	ISO 1133	12	g/10min
<b>Mechanical</b>				
Flexural Modulus	@23°C	ISO 178	1400	MPa
Tensile Strength	@Yield	ISO 527-1,-2	34	MPa
Izod impact strength, Notched	@+23°C	ISO 180/1A	3.7	kJ/m <sup>2</sup>
Charpy Impact Strength, notched	@+23°C	ISO 179/1eA	3	kJ/m <sup>2</sup>
<b>Thermal</b>				
HDT	@0.45 MPa	ISO 75/B	90	°C

- The values given are typical values measured on the product and should not be considered as specification

## Compliance to Regulations on Medical use

Eltex® MED 100-MG12

- complies with European Pharmacopeia Monographs 3.1.3 and 3.1.6
- meets the requirements of the USP 29, <88> guideline concerning the biological reactivity test in vivo (so-called USP class VI)



# Eltex® MED 100-MG12

## Storage and handling

The product should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage conditions can impart physical properties of the product and initiate degradation resulting potentially in odour generation and colour changes.

## Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, send an email to [psnohreg@ineos.com](mailto:psnohreg@ineos.com).

## Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Material Safety Data Sheet (MSDS) that may be obtained from the website [www.ineospolyolefins.com](http://www.ineospolyolefins.com). Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

## Exclusion of Liability

Although INEOS O&P Europe endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS O&P Europe is accurate and up to date, no representation or warranty, express or implied is made by INEOS O&P Europe as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS O&P Europe are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS O&P Europe materials are suitable for the particular purpose intended and INEOS O&P Europe shall not be responsible for any loss or damage caused by misuse of INEOS O&P Europe products. To the maximum extent permitted by law, INEOS O&P Europe accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS O&P Europe materials or the use of INEOS O&P Europe materials in conjunction with such other materials.