

## PRODUCT INFORMATION

Glass fiber reinforced Grade

# KOPA<sup>®</sup> KN333G25BL

Polyamide 66 Compound resin

Glass fiber reinforced grade

Property	Test Method	Units	Value
<b>Physical</b>			
Specific Gravity	ASTM D792	-	1.32
Shrinkage	ASTM D955	%	0.4~0.7
Water Absorption 23°C, Equilibrium 60%RH	ASTM D570	%	0.4
<b>Thermal</b>			
Melting Point	ASTM D3418	°C	255
Heat Deflection Temperature under Load	ASTM D648		
HDT/A 0.45 MPa ( 4.6 kg/cm <sup>2</sup> )		°C	250
HDT/A 1.82 MPa ( 18.6 kg/cm <sup>2</sup> )		°C	247
Coeff. Of Linear Thermal Expansion	ASTM D696	× 10 <sup>-5</sup> cm/cm·°C	0.2
Flammability	UL 94		HB
<b>Mechanical</b>			
Tensile Strength 23°C	ASTM D638	kg/cm <sup>2</sup>	184(1800)
Tensile Elongation 23°C	ASTM D638	%	7
Flexural Strength 23°C	ASTM D790	kg/cm <sup>2</sup>	255(2500)
Flexural Modulus 23°C	ASTM D790	kg/cm <sup>2</sup>	7245(71000)
Notched Izod Impact Strength 23°C	ASTM D256	kg cm/cm	98(10)
Rockwell Hardness R scale	ASTM D785	g/cc	121
<b>Electrical</b>			
Arc Resistance	ASTM D495	sec	135
Dielectric Constant	ASTM D150	10 <sup>6</sup> Hz	3.6
Dielectric Strength	ASTM D149	KV/mm	21

The information provided in this data sheet is based on our present state of knowledge and is estimated by KOLON PLASTICS, Inc. This information should not be used as guaranteeing specification limits. KOLON PLASTICS, Inc. make no warranty and liability in connection with any use of this information.



**KOLON PLASTICS, Inc.**

KOLON TOWER, 1-23, BYULYANG-DONG, GWACHEON-CITY GYUNG GI-DO, KOREA

More information : [www.kolonplastics.com/enghome](http://www.kolonplastics.com/enghome)