

Lustran SAN Sparkle

Styrene Acrylonitrile (SAN)

TECHNICAL
DATASHEET

DESCRIPTION

Lustran® SAN Sparkle is a transparent styrene acrylonitrile (SAN) with high flow and toughness and glass-like clarity

FEATURES

- Chemical and heat resistance
- Meets USP Class VI requirements
- Meets FDA modified ISO 10993-1 requirements requirements
- UL classification 94 HB

APPLICATIONS

- Medical devices
- Cosmetic packaging
- Housewares
- Personal care

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Flow Rate, 230 °C/3.8 kg	ASTM D 1238	g/10 min	12
Mechanical Properties			
Izod Notched Impact Strength, 23 °C (73 °F)	ASTM D 256	ft-lb/in	0.4
Izod Unnotched Impact Strength	ASTM D 256	ft-lb/in	3
Tensile Stress at Break, 23 °C	ASTM D 638	psi	9000
Tensile Modulus	ASTM D 638	psi x 10 ³	470
Flexural Strength, 23 °C	ASTM D 790		14000
Flexural Modulus, 23 °C	ASTM D 790	psi x 10 ³	500
Hardness, Rockwell	ASTM D 785	M scale	75
Thermal Properties			
Vicat Softening Temperature, B/1 (120 °C/h, 10N)	ASTM D 1525	°F	226
DTUL @ 264 psi - Unannealed	ASTM D 648	°F	200
DTUL @ 264 psi - Annealed	ASTM D 648	°F	216
Coefficient of Linear Thermal Expansion	ASTM D 696	10 ⁻⁴ /°F	0.38
Optical Properties			
Refractive Index, Sodium D Line	ASTM D 542	-	1.57
Light Transmission at 550 nm	ASTM D 1003	%	89 - 90

Property, Test Condition	Standard	Unit	Values
Haze	ASTM D 1003	%	0.7
Other Properties			
Density	ASTM D 792	lb/in ³	1.08
Processing			
Melt Temperature Range	-	°F	425 - 500
Mold Temperature Range	-	°F	100 - 180
Drying Temperature	-	°F	180 - 190

Typical values for uncolored products

SUPPLY FORM

Lustran SAN resins are available in bulk railcar, bulk truckload and 726kg box quantities.

REGULATORY COMPLIANCE

Please refer to Styrolution web site or contact Styrolution Technical Service for further information.

FOOD CONTACT COMPLIANCE STATEMENT

The base resin used in the Lustran SAN Sparkle product is in chemical compliance with 21 CFR 181.32 (acrylonitrile copolymers and resins) for use in the manufacture of repeated usehouseware articles.

PRODUCT SAFETY

Please refer to Styrolution product SDS or contact Styrolution Technical Service for further information.

DISCLAIMER

The aforementioned data shall constitute the agreed contractual quality of the product sold by INEOS Styrolution at the time of passing of risk. INEOS Styrolution does not make any further warranty, representation or guarantee of any kind, express or implied, regarding the suitability of the product for any particular purpose or application and INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.