

## LUSTRAN<sup>®</sup> SAN 29

### SAN

Specialty Grade

#### Description

Lustran SAN 29 resin is an injection molding grade of transparent SAN (styrene acrylonitrile) thermoplastic. The base resin used in the Lustran SAN 29 product is in chemical compliance with 21 CFR 181.32 (acrylonitrile copolymers and resins) for use in the manufacture of repeated-use houseware articles. Lustran SAN 29 resin has the highest impact strength of the grades used for houseware articles in the Lustran SAN product line. Lustran SAN 29 in our standard tint (color code 552160) also meets U.S. Pharmacopeia 23 Class VI and ISO 10993-1 based on biocompatibility testing of the base polymer with higher levels of additives and colorants than used in this formulation. Lustran SAN 29 has a large molding window and is easy to process.

#### Applications

Lustran SAN 29 resin is used in applications requiring better impact strength than general purpose SAN. Typical applications include tumblers, water pitchers, blender jars, water filter housings, and battery cases.

Lustran SAN 29 performs exceptionally well in applications that are subject to demanding environments. Finished products are resistant to heat deformation, scratching, and chemicals, such as foodstuffs, oils, greases, acids, alkalies, and petroleum products. Common solvents, such as MEK and THF, can be used for bonding Lustran SAN 29. Parts molded out of Lustran SAN 29 resin also accept various methods of printing. As with any product, use of Lustran SAN 29 resin in a given application must be tested (including field testing, etc.) in advance by the user to determine suitability.

#### Drying

Drying prior to processing in a desiccant dehumidifying hopper dryer is recommended. An inlet air dew point of -20°F (-29°C) or below is recommended to achieve a moisture content of ≤0.2%. Typical drying conditions are 2 hours at 180°-190°F (82°-88°C). Drying for 4 hours at 160°-170°F (71°-77°C) is also adequate.

#### Processing

A reciprocating screw injection molding machine is preferred. A general-purpose screw with a 2.5:1 compression ratio is suggested. A minimum L/D ratio of 20:1 will ensure melt homogeneity.

Use minimum melt temperature with minimum barrel residence time, consistent with good part quality. To avoid excessive residence time, volume and weight of the shot should be balanced against barrel capacity and injection stroke. A shot weight-to-machine ratio capacity of 0.5–0.7 is recommended. A mold temperature of 120-180°F (50-80°C) is recommended for development of maximum gloss and strength.

Undercuts must be avoided when processing SAN. To avoid mold release problems, a minimum draft of 1° should be specified.

Typical processing parameters are noted below. Actual processing conditions will depend on machine size, mold design, material residence time, and shot size.

<b>Typical Injection Molding Conditions*</b>	
Barrel Temperatures:	
Rear.....	340°– 365°F (170°– 185°C)
Middle.....	365°– 390°F (185°– 200°C)
Front.....	395°– 420°F (200°– 215°C)
Nozzle.....	395°– 420°F (200°– 215°C)
Melt Temperature.....	425°– 500°F (220°– 260°C)
Mold Temperature.....	100°– 180°F (40°– 80 °C)
Injection Pressure.....	10,000 – 20,000 psi
Hold Pressure.....	.40 – 80% of Injection Pressure
Back Pressure.....	.0 – 25 psi
Screw Speed.....	Moderate
Injection Speed.....	Moderate to High
Cushion .....	1/8 in max
Clamp.....	.2 – 4 ton/in <sup>2</sup>

*\*Extended barrel soak time at start-up or short-term shutdown (up to 6 hours) will change color of material in barrel.*

Additional information on processing may be obtained by contacting a INEOS ABS technical service representative.

### **Regrind Usage**

For Lustran SAN resin, up to 20% regrind may be used with virgin material, depending upon the end-use requirements of the molded part and provided that the material is kept free of contamination and is properly dried (see section on Drying). Any regrind used must be generated from properly molded parts, sprues, and/or runners. All regrind used must be clean, uncontaminated, and thoroughly blended with virgin resin prior to drying and processing. Under no circumstances should degraded, discolored, or contaminated material be used for regrind. Materials of this type should be discarded.

Improperly mixed and/or dried regrind may diminish the desired properties of Lustran SAN resin. It is critical that you test finished parts produced with any amount of regrind to ensure that your end-use performance requirements are fully met. Regulatory or testing organizations (e.g., UL) may have specific requirements limiting the allowable amount of regrind. Because third party regrind generally does not have a traceable heat history, nor offer any assurance that proper temperatures, conditions, and/or materials were used in processing, extreme caution must be exercised in buying and using regrind from third parties.

*The use of regrind material should be avoided entirely in those applications where resin properties equivalent to virgin material are required, including but not limited to color quality, impact strength, resin purity, and/or load-bearing performance.*

### **Health and Safety Information**

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling the INEOS ABS products mentioned in this publication. For materials mentioned which are not INEOS ABS products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be followed. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., *material safety data sheets and product labels*. Consult your INEOS ABS representative or contact the Product Safety and Regulatory Affairs Department at INEOS ABS.

### **\*\*Regulatory Compliance Information:**

Some of the end uses of the products described in this publication must comply with applicable regulations, such as the FDA, NSF, USDA, CPSC and BfR. If you have any questions on the regulatory status of these products, contact your INEOS ABS representative or Regulatory Affairs Manager at INEOS ABS.

Typical Properties* for Standard Tint (552160) Resin	ASTM Test Method (Other)	Lustran® SAN 29 Resin	
		U.S. Conventional	SI Metric
<b>General</b>			
Specific Gravity	D 792		1.07
Density	D 792	0.039 lb/in <sup>3</sup>	1.07 g/cm <sup>3</sup>
Specific Volume	D 792	25.9 in <sup>3</sup> /lb	0.93 cm <sup>3</sup> /g
Mold Shrinkage	D 955	0.003 - 0.004 in/in (mm/mm)	
Melt Flow Rate at 230°C/3.8-kg Load	D 1238	5 g/10 min	
<b>Optical</b>			
Transmittance at 0.125-in (3.2-mm) Thickness	D 1003	87 - 88%	
Haze at 0.125-in (3.2-mm) Thickness	D 1003	0.8%	
Refractive Index	D 542	1.57	
<b>Mechanical</b>			
Tensile Stress at Break	D 638	10,800 lb/in <sup>2</sup>	74 MPa
Flexural Stress at Yield	D 790	18,900 lb/in <sup>2</sup>	130 MPa
Flexural Modulus	D 790	500,000 lb/in <sup>2</sup>	3.4 GPa
Impact Strength:			
0.125-in (3.2-mm) Thickness			
Notched Izod	D 256	0.4 ft-lbs/in	21 J/m
Unnotched	D 4812	4.7 ft-lbs/in	251 J/m
Deformation Under Load:	D 621		1.5%
4,000 psi (28 MPa), 122°F (50°C), 24 Hr			
Rockwell Hardness	D 785	83 (M Scale)	
<b>Thermal</b>			
Deflection Temperature Under Load:	D 648		
0.5-in (12.7-mm) Thickness			
Unannealed, 264 psi (1.82 MPa)		205°F	96°C
Relative Temperature Index:	(UL746B)		
0.059-in (1.5-mm) Thickness			
Electrical		122°F	50°C
Mechanical with Impact		122°F	50°C
Mechanical without Impact		122°F	50°C
Coefficient of Linear Thermal Expansion	D 696	3.8 E-05 in/in/°F	6.8 E-05 mm/mm/°C
Vicat Softening Temperature, Rate B	D 1525	232°F	111°C
<b>Flammability**</b>			
UL94 Flame Class:	(UL94)		
0.059-in (1.5-mm) Thickness			HB***
0.118-in (3.0-mm) Thickness			HB***

\* These items are provided as general information only. They are approximate values and are not part of the product specifications.

\*\* Flammability results are based on small-scale laboratory tests for purposes of relative comparison and are not intended to reflect the hazards presented by this or any other material under actual fire conditions.

\*\*\* Clear color.

Note: The information contained in this publication is current as of August 2012. Please contact INEOS ABS to determine whether this publication has been revised.

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

**INEOS**  
**ABS**

INEOS ABS (USA) Corporation  
INEOS ABS NAFTA  
356 Three Rivers Parkway  
Addyston, OH 45001

[www.ineos-abs.com](http://www.ineos-abs.com)