



# Component - Plastics

File Number: E67171

LG CHEM LTD  
20 YOIDO-DONG  
YONGDUNGPO-GU  
SEOUL, 150-721 Republic of Korea



## LI921NS

Acrylonitrile Styrene Acrylate (ASA), pellets

Flammability	Value	Test Method
Glow Wire Flammability Index		IEC 60695-2-12
0.40 mm	725 °C	
0.75 mm	800 °C	
1.5 mm	700 °C	
3.0 mm	700 °C	
Glow Wire Ignition Temperature		IEC 60695-2-13
0.40 mm	750 °C	
0.75 mm	825 °C	
1.5 mm	725 °C	
3.0 mm	725 °C	
Thermal	Value	Test Method
RTI Elec		UL 746
0.40 mm	50.0 °C	
0.75 mm	50.0 °C	
1.5 mm	50.0 °C	
3.0 mm	50.0 °C	
RTI Imp		UL 746
0.40 mm	50.0 °C	
0.75 mm	50.0 °C	
1.5 mm	50.0 °C	
3.0 mm	50.0 °C	
RTI Str		UL 746
0.40 mm	50.0 °C	
0.75 mm	50.0 °C	
1.5 mm	50.0 °C	
3.0 mm	50.0 °C	