

HDPE for Film

YUHWA HIDEN F500

 Features
and Uses

Properties

Application	HDPE for Film			
Features	High Stiffness, Low Die-Deposit			
Uses	Shopping Bags, General Purpose, Industrial Uses			
	Items	Specification	Unit	Test Method
	Melt Index	0.07	g/10min.	ASTM D1238
	Density	0.956	g/cm ³	ASTM D1505
	Mold Shrinkage	1.5~2.5	%	KPIC Method
	Water Absorption	<0.01	%	ASTM D570
	Tensile Strength at Yield	370	kgf/cm ²	ASTM D638
	Elongation at Break	>500	%	ASTM D638
	Flexural Modulus	10,000	kgf/cm ²	ASTM D790
	Hardness (Rockwell)	46	R Scale	ASTM D785
	Impact Strength (Izod with Notch)	>50	kgf cm/cm	ASTM D256
	Environment Stress Cracking Resistance	>1,000	hr. Cond. B. 10%	ASTM D1693
	Melting Point	134	°C	ASTM D3418
	Softening Point (Vicat)	123	°C	ASTM D1525
	Heat Deflection Temperature	70	°C	ASTM D648
	Brittleness Temperature	<-70	°C	ASTM D746

※ Above data are intended to serve as guides only, and are not sales specification limits.

 Contact
Info.

Division	Team in charge	TEL	FAX	e-mail
International Trade	KPICC	82-2-3706-0844, 0849	82-2-3706-0893, 0894	trade@kpicc.com
Technical Service	Marketing Support Team	82-2-2122-1537	82-2-2122-1519	H15106@kpic.co.kr