



PRODUCT INFORMATION

NILENE P3 K30VA

Polypropylene homopolymer 30% glass fibres reinforced chemically coupled, low flow, good mechanical properties.

ISO short Form ISO 1043: PP-GF30 Pellets

Key Features

- Good impact - stiffness balance
- Designed for injection moulding applications
- Glass fibres reinforced

Availability

- YT: laser printable
- S: heat stabilized
- MT: long-term service stability for contact with copper
- AT: antistatic
- L: UV stabilized
- D: detergent stabilized
- All colours

Process

- INJECTION MOULDING

Application

- Household
- Furniture
- Electrical
- Consumer
- Building
- Automotive

Property	Method	Unit	Value	Condition	State
----------	--------	------	-------	-----------	-------

ELECTRICAL

Tracking Resistance (CTI - Method A)	IEC 60112	Volt	>600		
--------------------------------------	-----------	------	------	--	--

PHYSICAL

Density (+23°C)	ISO 1183	g/cm ³	1,12		
Filler content	ISO 3451	%	30	600°C - 1 h	
Water Absorption (24h / +23°C)	ISO 62	%	0,2		
Mould Shrinkage (Parallel)	Internal method	%	0,2-0,4		



PRODUCT INFORMATION

NILENE P3 K30VA

Mould Shrinkage (Normal)	Internal method	%	0,7-0,9
--------------------------	-----------------	---	---------

Melt Flow Rate (MFR)	ISO 1133	g/10 min	3	230°C - 2,16 kg
----------------------	----------	----------	---	-----------------

MECHANICAL

Tensile Modulus	ISO 527-1,2	MPa	6000	Speed 1 mm/min
-----------------	-------------	-----	------	----------------

Elongation at Break	ISO 527-1,2	%	3,5	Speed 50 mm/min
---------------------	-------------	---	-----	-----------------

Tensile Break Strength	ISO 527-1,2	MPa	90	Speed 50 mm/min
------------------------	-------------	-----	----	-----------------

Flexural Modulus	ISO 178	MPa	5600	Speed 1 mm/min
------------------	---------	-----	------	----------------

Flexural Break Strength	ISO 178	MPa	125	Speed 1 mm/min
-------------------------	---------	-----	-----	----------------

IZOD Notched Impact	ASTM D256	J/m	90	+23°C
---------------------	-----------	-----	----	-------

CHARPY Unnotched Impact (+23°C)	ISO 179/1eU	kJ/m ²	70
---------------------------------	-------------	-------------------	----

THERMAL

Softening Temperature - 1 kg (VST/A/50)	ISO 306	°C	155
---	---------	----	-----

Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	134
---	---------	----	-----

Deflection Temperature 1,80 MPa (HDT A)	ISO 75A	°C	148
---	---------	----	-----

Deflection Temperature 0,45 MPa (HDT B)	ISO 75B	°C	156
---	---------	----	-----

FLAMMABILITY

Flame Behaviour (1,6 mm)	UL94	Class	HB
--------------------------	------	-------	----

Burning Rate (US-FMVSS 302)	ISO 3795	mm/min	< 100	Thickness 2 mm
-----------------------------	----------	--------	-------	----------------

Oxygen index	ASTM D2863	%	20
--------------	------------	---	----

INJECTION MOULDING

Value

Drying Temperature (Circulating Air Oven)	80 - 100°C
---	------------

Drying Temperature (Desiccant Dryer)	80 - 100°C
--------------------------------------	------------

Drying Time (Circulating Air Oven)	3 - 6 hours
------------------------------------	-------------

Drying Time (Desiccant Dryer)	2 - 4 hours
-------------------------------	-------------

Suggested Max Moisture	0,2%
------------------------	------

Suggested Max Re grind	< 10%
------------------------	-------

Melt Temperature	220 - 250°C
------------------	-------------

Feed Temperature	50°C
------------------	------



PRODUCT INFORMATION

NILENE P3 K30VA

Rear Temperature	200°C
Middle Temperature	220°C
Front Temperature	230°C
Nozzle Temperature	240°C
Mould Temperature	40 - 60°C
Injection Rate	50 - 150 mm/sec
Injection Pressure	60 - 120 Mpa
Packing Pressure	30 - 80 Mpa
Back Pressure	As low as possible (<0,5 MPa)
Screw Revolving Speed	30 - 80 rpm
Cushion	5 - 8 mm
Vent Depth	0,05 mm

Notes It is normally not necessary to dry NILENE compounds, however should there be surface moisture (condensate) on the moulding compound as a result of incorrect storage, drying process is required. NILENE must be stored indoors at a temperature below 40°C avoiding humidity and direct sunlight as well. NILENE can be processed on a standard injection moulding unit. A general purpose metering screw is recommended with a zone distribution of 40% feed, 40% transition and 20% metering. When the heating cylinder is completely purged of NILENE material the machine may be shut down.