

HDPE PE100

YUHWA HIDEN P600 BL

 Features
and Uses

Application	HDPE PE100
Features	PE100, Excellent Creep Resistance, SCG, RCP, Color:Black
Uses	Gas Pipes, Water Supply and Drain Pipes

Properties

Items	Specification	Unit	Test Method
Melt Index (5kg)	0.23	g/10min.	ASTM D1238
Density	0.961	g/cm ³	ASTM D1505
Tensile Strength at Yield	230	kgf/cm ²	ASTM D638
Elongation at Break	>600	%	ASTM D638
Flexural Modulus	9,500	kgf/cm ²	ASTM D790
Hardness (Rockwell)	62	shore D	ASTM 2240
Impact Strength (Izod with Notch)	>50	kgf cm/cm	ASTM D256
Environment Stress Cracking Resistance	>5,000	hr, F50	ASTM D1693
Melting Point	130	℃	ASTM D3418
Softening Point (Vicat)	124	℃	ASTM D1525
Oxidation Induction Time at 200°C	>60	min	ASTM D3895
Heat Deflection Temperature	65	℃	ASTM D648
Brittleness Temperature	<-70	℃	ASTM D746
Carbon Black Content	2.3	%	ISO 6964
Carbon Black dispersion	<3	Grade	ISO 18553

※ Above data are intended to serve as guides only, and are not sales specification limits.

 Contact
Info.

Division	Team in charge	TEL	FAX	e-mail
International Trade	KPICC	82-2-3706-0844, 0849	82-2-3706-0893, 0894	trade@kpicc.com
Technical Service	Marketing Support Team	82-2-2122-1537	82-2-2122-1519	H15106@kpic.co.kr