

TRICAP[®] OC35T PN

Organosheet

PROPERTY	UNIT	TYPICAL DATA
Material	-	PC CF(Twill)
Fiber Contents	Vol %	48
Specific Gravity	-	1.49
Tensile Strength	MPa	750
Tensile Modulus	GPa	48
Flexural Strength	MPa	810
Flexural Modulus	GPa	45
Note	-	Flame Retardant

※ The figures listed in this table are typical values obtained under the standard test methods and may not be applicable for products that are under different application condition.

Global Network**HEAD OFFICE**

Samyang Corporation
31, Jong-ro 33-gil, Jongno-gu, Seoul, Korea
T. +82-2-740-7747

Chemical Research Center

730, Daedeok-daero, Yuseong-gu, Daejeon, Korea
T. +82-42-865-8114

DAEJEON ENGINEERING PLASTIC PLANT

9 Yuseong-daero, 1366-gil, Yuseong-gu, Daejeon, Korea
T. +82-42-867-3800

SAMYANG ENGINEERING PLASTICS (SHANGHAI) CO., LTD.

No.131, Shuangying Road, Qingpu Industrial Area,
Qingpu County, Shanghai, China
T. +86-21-6922-2270

SAMYANG ENGINEERING PLASTICS (GERMANY) CO., LTD.

8 Taunusanlage Frankfurt am Main,
HE 60329, Germany 855
T. +49 (0)162-579-6639