

TECHNICAL DATA SHEET

Clearflex® CH D0

Versalis S.p.A
(PE-VLD)

Processing

Film extrusion

Delivery Form

Pellets

Features

Blending resin, Soft feel

Chemical Resistance

Oxidation resistance

Processing/Physical Characteristics	Value	Unit	Standard
Melt flow index, MFI	2	g/10min	ISO 1133
Temperature	190	°C	
Load	2.16	kg	
Thermal Properties	Value	Unit	Standard
Melting temperature, 10°C/min	115	°C	ISO 11357-1/-3
Coeff. of linear therm. expansion, parallel	43	E-6/K	ISO 11359-1/-2
Optical Properties	Value	Unit	Standard
Gloss, 45°	80		ISO 2813
Haze	4		ISO 14782
Other Properties	Value	Unit	Standard
Density	900	kg/m ³	ISO 1183
Film Properties	Value	Unit	Standard
Stress at yield, parallel	5	MPa	ISO 527-3
Stress at yield, normal	5	MPa	ISO 527-3
Stress at break, normal	31	MPa	ISO 527-3
Maximum strain, parallel	600	%	ISO 527-3
Maximum strain, normal	850	%	ISO 527-3
Dynamic coefficient of friction	0.5		ISO 8295
Type of extrusion	cast		
Thickness of specimen	0.023	mm	