

TECHNICAL DATA SHEET

Clearflex® CL B0

Versalis S.p.A
(PE-VLD)

Processing

Film extrusion

Delivery Form

Pellets

Features

Blending resin, Soft feel

Chemical Resistance

Oxidation resistance

Processing/Physical Characteristics	Value	Unit	Standard
Melt flow index, MFI	3	g/10min	ASTM D 1238
Temperature	190	°C	
Load	2.16	kg	
Thermal Properties	Value	Unit	Standard
Melting temperature	118	°C	ASTM D 3418
Vicat temperature	80	°C	ASTM D 1525
Optical Properties	Value	Unit	Standard
Gloss	70		ASTM D 2457
Haze	6	%	ASTM D 1003
Other Properties	Value	Unit	Standard
Density	911	kg/m ³	ASTM D 792