

Absolac XT04P

Acrylonitrile Butadiene Styrene (ABS)

TECHNICAL DATASHEET

DESCRIPTION

Absolac® XT04 is a high heat grade

FEATURES

- High Heat grade

APPLICATIONS

- Automotive interior & exterior parts
- Lamp Housing
- Coffee Warmer
- Hair Dryer parts
- Microwave oven housings
- Irons

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Flow Rate, 220 °C/10 kg	ISO 1133	g/10 min	4
Mechanical Properties			
Izod Notched Impact Strength, 1/4" bar, 0.010" Notch Radius, 23 °C (73 °F)			> 18
Tensile Stress at Yield, 23 °C	ISO 527	MPa	55
Tensile Modulus (MD)	ISO 527	MPa	2800
Flexural Strength, 23 °C	ISO 178	MPa	70
Flexural Modulus, 23 °C	ISO 178	MPa	2400
Hardness, Rockwell	ISO 2039-2	R scale	106
Thermal Properties			
Vicat Softening Temperature, B/2 (120 °C/h, 50N)	ASTM D 1525	°C	108
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	102
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	105
Coefficient of Linear Thermal Expansion	ISO 11359	10 ⁻⁶ /°C	70 to 80
Optical Properties			
Specular Gloss, 60 °	ASTM D 523	%	+98
Other Properties			

Absolac XT04P

Acrylonitrile Butadiene Styrene (ABS)

TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Density	ISO 1183	kg/m ³	1040
Processing			
Linear Mold Shrinkage	ISO 294-4	%	0.45 to 0.65