

Styrolution PS 485N

High Impact Polystyrene (HIPS)

TECHNICAL DATASHEET

DESCRIPTION

Styrolution PS 485N is a high impact grade of polystyrene for extruded sheets with a matte surface.

FEATURES

- Matte surface
- UL 94 HB

APPLICATIONS

- Extruded parts with matte finish
- Fat resistant packaging

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate, 200 °C/5 kg	ISO 1133	cm ³ /10 min	4
Mechanical Properties			
Charpy Notched Impact Strength, 23° C	ISO 179/1eA	kJ/m ²	10
Tensile Stress at Yield, 23 °C	ISO 527	MPa	23
Tensile Strain at Yield, 23 °C	ISO 527	%	1.6
Tensile Modulus	ISO 527	MPa	1650
Elongation at Break (MD)	ISO 527	%	35
Flexural Strength, 23 °C	ISO 178	MPa	32
Thermal Properties			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	90
Coefficient of Linear Thermal Expansion	ISO 11359	10 ⁻⁶ /°C	80
Thermal Conductivity	ISO 22007-4	W/(m K)	0.17
Electrical Properties			
Dielectric Constant (100 Hz)	IEC 62631-2-1	-	2.5
Dissipation Factor (100 Hz)	IEC 62631-2-1	10 ⁻⁴	4
Dissipation Factor (1 MHz)	IEC 62631-2-1	10 ⁻⁴	4
Volume Resistivity	IEC 62631-3-1	Ohm*m	>10 ¹⁶
Surface Resistivity	IEC 62631-3-1	Ohm	>10 ¹³

Styrolution PS 485N

High Impact Polystyrene (HIPS)

TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Other Properties			
Density	ISO 1183	kg/m ³	1040
Processing			
Linear Mold Shrinkage	ISO 294-4	%	0.4 - 0.7
Melt Temperature Range	ISO 294	°C	180 - 260
Mold Temperature Range	ISO 294	°C	45
Injection Velocity	ISO 294	mm/s	200