

Zylar 765

Methyl Methacrylate Butadiene Styrene (MBS)

TECHNICAL DATASHEET

DESCRIPTION

Zylar® 765 is a MBS grade that provides very high toughness, good clarity and superior processing characteristics for demanding injection molding applications.

FEATURES

- High clarity
- High toughness
- Low density
- Gamma & ETO sterilizable

APPLICATIONS

- Appliance and consumer goods
- Office accessories
- Industrial housings and covers
- Displays
- Toys

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate, 200 °C/5 kg	ISO 1133	cm ³ /10 min	4.5
Melt Volume Rate 220 °C/10 kg	ISO 1133	cm ³ /10 min	48
Mechanical Properties			
Izod Notched Impact Strength, 23 °C	ISO 180/A	kJ/m ²	8
Charpy Notched Impact Strength, 23° C	ISO 179/1eA	kJ/m ²	15
Tensile Stress at Yield, 23 °C	ISO 527	MPa	23
Tensile Strain at Break, 23 °C	ISO 527	%	80
Tensile Modulus	ISO 527	MPa	1700
Thermal Properties			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	64
Vicat Softening Temperature, VST/A/120 (10N, 120 °C/h)	ISO 306	°C	94
Heat Deflection Temperature A; (unannealed; 1.8 MPa)	ISO 75	°C	60
Heat Deflection Temperature B; (unannealed; 0.45 MPa)	ISO 75	°C	72
Electrical Properties			
Optical Properties			
Refractive Index, Sodium D Line	ISO 489	-	1.57

Zylar 765

Methyl Methacrylate Butadiene Styrene (MBS)

TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Light Transmission at 550 nm	ASTM D 1003	%	90
Haze	ASTM D 1003	%	2
Other Properties			
Density	ISO 1183	kg/m ³	1050
Water Absorption, Saturated at 23 °C	ISO 62	%	0.1
Moisture Absorption, Equilibrium 23 °C/50% RH	ISO 62	%	0.05
Processing			
Melt Temperature Range	ISO 294	°C	200 - 240
Mold Temperature Range	ISO 294	°C	30 - 55
Rear Temperature Range	-	°C	180 - 210
Middle Temperature Range	-	°C	185 - 220
Front Temperature Range	-	°C	190 - 225
Drying Temperature	-	°C	65
Drying Time	-	h	2